

TECHNICAL DATA SHEET

SOY WAX 10

CHARACTERISTICS	METHOD	VALUES		
		MIN	MAX	TYPICAL
COLOR	Visual	OFF WHITE		
DROP POINT °C	DGF M-III 4a	34	40	
MELTING POINT °C	DGF M-III 3	50	56	
VISCOSITY mPa.s at 53 °C	R2 at 50rpm			442

Blend of soy wax especially developed for the production of candles in glass.

Recommended filling temperature, when ambient temperature:

Lower or equal to 18°C: between 70°C to 80°C.

Higher than 18°C: between 63°C to 67°C.

The glass should not be too cold.

If the glass has a diameter bigger than 7 or 8cm, it is advisable to make a second filling, 2 hours later, at the same temperature, on 1 to 2mm.

PRESENTATION: Flakes in boxes of 15kg,
or Slabs of 5kg in boxes of 20kg

Last revision: December 2021